

Product Code	AKPEROX BP50 POWDER
Description	DiBenzoyl Peroxide 50% with plasticizer
Specifications;	
Appearance	: White, Powder form
Active Oxygen Content	: 3,3% min.
Density	: 0,62 kg/lit
Peroxide Content	: 50%
SADT	: 60 °C
CAS Nr	: 94-36-0
UN Nr	: 3104
Applications	AKPEROX BP 50 used to harden unsaturated polyester (UP) resins at elevated temperatures as a sole catalyst.
Usage & Amount	Recommended to be used 1% – 3% in general, according to climate conditions and product formulation.
Packaging	25 kgs Carton Box
Handling & Storage	Must be kept between +5 C and +30 C. Keep pails tightly closed. Store and handle in a dry, well-ventilated place, away from sources of heat, ignition and direct sunlight in original packaging. Provide grounding and venting in order to prevent static electricity build-up. Avoid any contact with Amine and Cobalt Accelerators, acids, alkalis and heavy metal compounds such as driers and metal soaps.
Shelf Life	3 Months For unopened packages at recommended storage conditions

