

Matting Agent XG610B

I Description

XG610B is a kind of compound matting agent containing carboxyl, it reacts with epoxy as 1:2. The powder coatings formulated with XG610B has the excellent impact properties, flowing and yellowing resistance. The application of XG610B to the 50/50 or 60/40 resin could decrease the gloss effectively.

II Technical data

XG610B	Test Method	Specification
Appearance	Visualization	White powder
Softening Point	GB/T 4507-1999	110~150 °C
Solid Content	GB/T 1725-2008	99.0%min

III Application:

- The dosage of XG610B is 3~5%. Esp. suit for smooth matt finishes with 3~15% gloss (60°).
- As the gloss is connected with the resin used, the formulation should be tested in lab first. Coatings formulated with Guanghua P5078, ShenJian SJ 5#A(4:6), TianSong TM9011F (5:5), Quanfeng 9402 (4:6) can provide lower gloss and good impact properties.
- It is not recommended to add catalysts such as imidazole in the formula to improve the impact properties, as which may lead to gloss and flow fluctuation. .
- Baking Condition: 190°C/15min, or 200°C/12min.

IV Recommended Formula

S.N		RM	Supplier	F1	F2	F3	F4	
1	E-12	Epoxy Resin	SSC	145	145	124	124	
2	TM9011F	Polyester Resin	TianSong	105	-	-	-	
3	P5086	Polyester Resin	Sino-French	-	105	-	-	
4	SJ5#A	Polyester Resin	Shenjian	-	-	126	-	
5	P9402	Polyester Resin	Quanfeng	-	-	-	126	
6	XG610B	Matting Agent	SSC	20	20	20	20	
7	GLP588	Leveling Agent	SSC	5	5	5	5	
8	BLC701B	Leveling Additive	SSC	4	4	4	4	
9	Benzoin	Degassing Agent	SSC	2	2	2	2	
10	C	Carbon Black	Pigement	0.2	0.2	0.2	0.2	
11	NTR760	TiO ₂	Pigement	80	80	80	80	
12	W-44HB	BaSO ₄	Filler	138.8	138.8	138.8	138.8	
Total				500	500	500	500	
Gloss				60°	3.60%	3.80%	3.70%	4.00%
Film Thickness				µm	60-80	60-80	60-80	60-80
Impact(Direct/Reverse)				kg.cm	50	50	50	50

*Baking Condition: 190°C/15min

V Package, Storage & Handling

Available in polyethylene-lined, multi-ply paper bags, N.W.25KGS/Bag.
 Keep in the cool and dry place, keep away from fire.

